

Avery Dennison® DOL 1400Z Series Clear Laminate

Transparent Synthetic

Revision: 0 Dated: 05/11/16

Uses:

Avery Dennison DOL 1400Z Series Clear Cast Vinyl is a premium quality, ultra-thin, super-conformable cast vinyl film designed to be used with MPI 1105 SuperCast Series media for the most difficult 3D applications. The film serves as a protective overlamine film for solvent, UV, latex digital inks. DOL 1400Z Series offers an exceptional value for applications requiring ultimate conformability, abrasion resistance, and durability. The gloss film now features a synthetic liner that creates a super smooth high gloss finish which provides an overall paint like finish of printed graphics.



Face: 1.3 mil (32 microns) high gloss cast film



Adhesive: Permanent Acrylic (clear)



Liner: 2 mil Transparent Synthetic



Durability: Up to 4 years

Application Surfaces:

Flat, Flat with Rivets, Corrugations, Complex Curves, Deep Recesses (Extreme vehicle wraps)

Features:

- High gloss finish
- Super conformable face with excellent conformability
- Provides ultimate conformability for extreme vehicle wrap applications (i.e. deep recesses, compound curves, etc.)
- Protects image from scratches
- Enhances color and depth of image
- Outstanding durability and outdoor performance
- Dimensionally stable mottle reduction liner for easy converting & high gloss performance.
- Excellent dimensional stability
- Aids in application of printed graphic
- When paired with MPI SuperCast, no primer is required in deep recess channel areas
- Excellent UV, temperature, humidity, and salt-spray resistance

Conversion:

- Cold Overlaminating

Common Applications:

- Fleet
- Vehicle(Extreme wraps)
- Marine/ Watercraft
- Backlit Signs
- Wall Murals
- POP/ Tradeshow
- Window Graphics
- Outdoor Signage

Product Data Sheet

Page 1 of 3



Graphics Solutions



800.253.1569 | wensco.com

graphics.averydennison.com
Customer Service: 800-282-8379

Avery Dennison[®] DOL 1400Z Series

Clear Laminate

Transparent Synthetic

Revision: 0 Dated: 05/11/16

Physical Characteristics:

Property	Typical Value
Caliper, face	1.3 mil (32µm)
Caliper, adhesive	1.0mil (25 µm)
Dimensional stability	<0.015"(0.4mm)
Tensile at Yield	3.0 - 7.0 lb/in (0.5–1.25 kg/cm)
Elongation	150% min.
Hunter Gloss	Measured @ 60°
	DOL 1460Z - 90
Adhesion: 15 min.	3.0 lbs/in (525 N/m)
24 hr.	3.5 lbs/in (613 N/m)
Flammability	Self Extinguishing
Shelf-Life	2 years from date of manufacture when stored at the following temperatures and humidity conditions 68°-77° F (20° - 25° C) and 50±5% R. H.
Durability	Vertical Exposure
	Up to 4 years
Min. Application Temperature	40° F (4° C)
Service Temperature	-40° to 180 °F (-40° to 82° C) (Reasonable range of temperatures which would be expected under normal environmental conditions).
Chemical resistance	Resistant to most mild acids, alkalis, and salt solutions including water.

Data represents average values where applicable, and is not intended for specification purposes.

Warranty:

This Warranty applies to the Product listed in this Data Sheet. All statements, technical information (including physical and chemical characteristics) and recommendations about Avery Dennison products are based upon tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold subject to the Purchaser's assent and agreement that Purchaser is responsible for, and has independently determined, the suitability of such products for its purposes or its customer's purposes. Avery Dennison products are warranted to be free from defects in material and workmanship (i) for two years from the date of manufacture, or (ii) from the date of manufacture until the expiration of the period stated on the specific Product Data Sheet in effect at the time of delivery. Such time periods are subject in either case to the proper storing and application of said product, and the failure to properly store or apply the product, including without limitation the failure to follow any applicable Instructional Bulletin, negates any warranty. It is expressly agreed and understood that Avery Dennison's sole obligation and Purchaser's exclusive remedy under this warranty, under any other warranty, express or implied, or otherwise, shall be limited exclusively to: (a) repair or replacement of defective product without charge at Avery Dennison's plant or at the location of the product (at Avery Dennison's election), or (b) in the event repair or replacement are not commercially practical, a credit amount up to the price of the product taking into account the defect in the product in Avery Dennison's sole discretion.

THE WARRANTY EXPRESSLY SET FORTH ABOVE IS IN LIEU OF ANY OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTIES OF MERCHANTABILITY, FITNESS FOR ANY PARTICULAR USE AND/OR NON-INFRINGEMENT. SELLER SPECIFICALLY DISCLAIMS AND EXCLUDES ALL OTHER SUCH WARRANTIES. NO WAIVER, ALTERATION, ADDITION OR MODIFICATION OF THE FOREGOING CONDITIONS SHALL BE VALID UNLESS MADE IN WRITING AND MANUALLY SIGNED BY AN OFFICER OF AVERY DENNISON.

AVERY DENNISON'S LIABILITY FOR DEFECTIVE PRODUCTS SHALL NOT EXCEED THE PURCHASE PRICE PAID THEREFORE BY PURCHASER AND IN NO EVENT SHALL AVERY DENNISON BE RESPONSIBLE FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES WHETHER FORESEEABLE OR NOT, CAUSED BY DEFECTS IN SUCH PRODUCT, WHETHER SUCH DAMAGE OCCURS OR IS DISCOVERED BEFORE OR AFTER REPLACEMENT OR CREDIT, AND WHETHER OR NOT SUCH DAMAGE IS CAUSED BY AVERY DENNISON'S NEGLIGENCE.

All sales and contracts for sale of Products are subject to Purchaser's assent and agreement to this Warranty. Avery Dennison hereby objects to any terms or conditions contained in any purchase order or other communication of any kind from the Purchaser that is conflicting, inconsistent or additional to this Agreement.

Product Data Sheet

Page 2 of 3



Graphics Solutions

graphics.averydennison.com
Customer Service: 800-282-8379

Avery Dennison® DOL 1400Z Series Clear Laminate

Transparent Synthetic

Revision: 0 Dated: 05/11/16

Special Considerations:

When overlaminating UV printed graphics: Heat assist and increasing lamination pressure when applying the overlaminate will reduce the silvering that can occur when laminating UV printed graphics. Do not exceed 115° F (46° C) on the top or bottom roll. Roll pressure up to 100 psi may be used. When applying the overlaminate in this manner, use the minimum amount of unwind tension on the overlaminate to reduce stretching during application.

Related Documents:

The following Avery Dennison® literature will provide complete information to the user for proper application, storage, and other requirements and is available upon request from your Avery Dennison® representative or from the Avery Dennison website (www.graphics.averydennison.com).

Document Title	Reference Number
Substrate Cleaning and Preparation	Instructional Bulletin #1.10
Storage, Maintenance, and Cleaning of PVC Films	Instructional Bulletin #1.20
Tips for Overlaminating, Premasking & Packaging Graphics	Instructional Bulletin #5.50
Removal Instructions	Instructional Bulletin #4.10

Revisions are italicized

Avery Dennison is a registered trademark of Avery Dennison Corporation

Product Data Sheet

Page 3 of 3



Graphics
Solutions

graphics.averydennison.com
Customer Service: 800-282-8379