

DRY ERASE PRODUCT CODE: 4-0101



PRODUCT DESCRIPTION

1.0-mil clear polypropylene overlamine. The face film is non-treated with write-on, write-off and dry erase capabilities

APPLICATIONS

- Dry-erase overlamine
- Gloss overlamine
- Make any printed sign dry-erase

FEATURES AND BENEFITS

- Dry-erase capabilities
- Economical dry-erase

TECHNICAL DATA

| | |
|------------------|-----------------------------------|
| Face Material | 1.0-mil polypropylene non-treated |
| Color and Finish | Clear gloss |
| Adhesive | 07, Permanent solvent |
| Liner | 50# bleached paper |

TYPICAL CHARACTERISTICS

| | | |
|--|-----------------|---------------|
| Target Adhesion Values | <u>15 min.</u> | <u>24 hr.</u> |
| (PSTC-1, 180° peel @ 12"/min., 73°F, on Stainless Steel) | 30 oz. | 40 oz. |
| Minimum Application Temperature | 50°F | |
| Service Temperature Range | -40°F to +180°F | |
| Shelf Life (@ 73°F, 50% RH) | 2 years | |
| Outdoor Durability (ASTM G53) | 1 year | |

CHEMICAL RESISTANCE

| | |
|---------------------------------|-----------|
| Distilled Water (24 hr) | No Effect |
| Detergent (24 hr) | No Effect |
| 10% HCl (10 min) | No Effect |
| 10% Ammonium Hydroxide (10 min) | No Effect |
| Anti-Freeze (24 hr) | No Effect |
| SAE 20 Motor Oil (24 hr) | No Effect |
| Gasoline (1 hr) | No Effect |

The above information is based on research believed to be reliable, but does not constitute a warranty. All material should be tested by the purchaser to determine suitability of the product for their purposes.

