

FASHION



PU



300°F - 320°F



PEEL : COLD



Flex Blade 45°
Medium Pressure



50-170 µm



15 - 20 Sec.

SPECIFICATIONS

APPLICATION

1. Cut the material in reverse with a Flex blade
2. Weed the excess material
3. Heat press on the garment at 300-320 ° F & Protect the polyester carrier with silicone paper 15 - 20 sec - medium pressure
4. Peel the carrier off when cold

THICKNESS:  Polyurethane 50 - 170 microns

CARRIER: Adhesive & Transparent polyester

CERTIFICATES:  Oeko-Tex Label Standard 100 Class II



APPLIES ON

Cotton • Polyester • Acrylic & Similar Fibres

CARE & MAINTENANCE

- Always respect the garment's instructions
- Allow 24 hours after application before washing
- Iron the backside only

WASH

- Max 140°F
- Preferably inside out
- Do not bleach
- Tumble-dry approved
- Dry-cleaning approved

STORE

- Up to 1 year
- In a dry room (60-85°F)
- Away from sunlight
- In vertical position

Chemica
Heat transfers for textiles