



► Series 3210 Overlamine

Premium Cast Overlamine Pressure-Sensitive Film

Series 3210 overlamine is constructed of a 1.3-mil (35 micron) gloss cast vinyl film with clear, permanent pressure-sensitive adhesive. Designed to protect printed images and prolong the life of the printed images. Series 3210 provides the same protection as our standard overlamines while having excellent conformability during installation with a lighter weight film. The gloss finish provides an extra pop to printed graphics. Series 3210 is rated for outdoor durability up to 7 years. This product is not designed to be used as an optically clear window film.

APPLICATIONS & FEATURES

- Protective overlamine for DPF 6100XLP, DPF 6000XRP, DPF 6000RP White, DPF 6000RP Clear, DPF 6500, DPF 6700, DPF 4600LX, DPF 4500GT/MT, DPF 8000 White, DPF 9000, DPF 4000, DPF 4300, Series 67A
- Fleet graphics, vehicle applications, long-term signage, kiosks and POP displays.
- UV inhibitors to protect and extend the life of your printed graphic.
- Arlon overlamine film is designed to be laminated cold without any heat.

PERFORMANCE & PHYSICAL DATA

PROPERTY	TEST METHODS	TYPICAL VALUE	
SURFACE FINISH	Gloss Meter 60° Reflection	80 to 90 Gloss Units	
THICKNESS	Micrometer, Federal Bench Type	1.3 mil (35 micron)	
TENSILE STRENGTH	Tensile Tester with 2-in (51 mm) jaw separation; crosshead speed of 12 in/min. (5.1 mm/s), web direction	≥ 6.5 lb/in	≥ 1.2 kg/cm
ELONGATION	Instron Tensile Tester as above	≥ 200%	
SHELF LIFE (IN BOX)	Ideal Storage Temperature 70°F (21°C) and 50% relative humidity	2 years from factory shipment	
APPLICATION TEMPERATURE RANGE	On clean, dry substrate		
	Flat:	40°F to 100°F	4.4°C to 38°C
	Corrugated with rivets & channels:	60°F to 100°F	15°C to 38°C
SERVICE TEMPERATURE RANGE	On clean, dry substrate	-40°F to 175°F	-40°C to 79°C
DIMENSIONAL STABILITY	Shrinkage After 158°F (70°C), 48 hours	< 10-mil	0.25 mm
PEEL ADHESION	PSTC-1, 15 min, 70°F (21°C)	3.0 lbs/in	0.535 kg/cm
LINER RELEASE	TLMI Release at 90°, 300 in/min (760 cm/min)	37 g/2in	7.28 g/cm

Standard Terms & Conditions Apply





TERMS & CONDITIONS

The following is made in lieu of all warranties expressed or implied:

All statements, technical information and recommendations published by Arlon relating to Arlon products are based on tests believed to be reliable and within the accuracy of the equipment used to obtain the specific values. Their accuracy or completeness is not guaranteed and Arlon makes no warranty with regard thereto. Seller's and manufacturer's only responsibility shall be to replace any quantity of the product proved defective. Seller and manufacturer shall not be liable for injury, loss or damage, direct or consequential, arising out of use or the inability to use the product. Nor shall seller or manufacturer be liable for any costs or expenses incurred in the processing or printing on the product. Before using, user shall determine the suitability of the product for its intended use. User assumes all risk and liability of every nature in connection therewith. No statements or recommendations other than those contained in the technical information published by Arlon shall have force or effect unless contained in an agreement manually signed by the officers of seller and manufacturer.

December 2017

USA:  200 Boysenberry Lane, Placentia, CA 92870, USA
EUROPE:  North Sea Building, Gevers Deynootweg 93, 4th Floor, 2586BK Den Haag, The Netherlands

 800 232 7161/+1 714 985 6300  800 329 2756
 +31 70 354 4311  +31 70 355 7721

arlon.com